

# Corax<sup>®</sup> HP130

Carbon black for Rubber - Corax Hard Grade



- 1.
2. Hysteresis 가



	(mg/g)	: 115
	(m <sup>2</sup> /g)	: 127
	(% vs IRB#3)	: 120
DBP	(cc/100g) DBP	: 135
	(% Max.)	: 0.75
가	(% Max.)	: 1.0
		: 7.0
	(kg/m <sup>3</sup> )	: 320
#325	(ppm, Max.)	: 300
#35	(ppm, Max.)	: 0



Tire Tread ( PC & TB )

DBP /Iodine

